

(19)



Europäisches Patentamt
European Patent Office
Office européen des brevets



(11) Publication number:

0 543 125 A1

(12)

EUROPEAN PATENT APPLICATION(21) Application number: **92116872.0**(22) Date of filing: **02.10.92**

(51) Int. Cl.⁵: **C08K 3/32, C08L 67/02,
C08L 69/00, //(C08L67/02,
69:00)(C08L69/00,67:02)**

(30) Priority: **20.11.91 NL 9101936**(43) Date of publication of application:
26.05.93 Bulletin 93/21(54) Designated Contracting States:
DE ES FR GB IT NL

(71) Applicant: **GENERAL ELECTRIC COMPANY**
1 River Road
Schenectady, NY 12345(US)

(72) Inventor: **Van Helmond, Johannes**
General Electric Plastics B.V., P.O. Box 117
NL-4600 AC Bergen op Zoom(NL)

(74) Representative: **Pratt, Richard Wilson et al**
London Patent Operation G.E. Technical
Services Co. Inc. Essex House 12/13 Essex
Street
London WC2R 3AA (GB)

(54) **Stabilized polyester-polycarbonate blends.**

(57) The invention relates to polymer mixtures which comprise a polyalkylene phthalate and an aromatic polycarbonate and/or a brominated aromatic carbonate oligomer, polymer or copolymer. It has been found that zinc or calcium hydrogen phosphates are good transesterification inhibitors. An important advantage of the said inhibitors is that they do not condense or hardly condense to polyphosphates and that they do not negatively influence the impact strength of the polymer mixture.

Best Available Copy

EP 0 543 125 A1

The invention relates to a polymer mixture which comprises

- A) a polyalkylene phthalate
- B) an aromatic polycarbonate or a brominated aromatic carbonate oligomer, polymer or copolymer or a mixture of a brominated aromatic carbonate oligomer, polymer or copolymer and a non-brominated aromatic polycarbonate, and
- C) a transesterification inhibitor.

The invention also relates to articles formed from the polymer mixture according to the invention.

Polymer mixtures which comprise a polyalkylene phthalate, an aromatic polycarbonate and a transesterification inhibitor are generally known, for example, from US-A-3,953,539. For example, according to US-A-3,953,539, the salts may be used of a large number of different metals with phosphorus-containing acids. As specific examples are mentioned salts of sodium, calcium, aluminium, potassium and magnesium.

It has unexpectedly been found that hydrogen phosphates of zinc or calcium show an important advantage compared with the corresponding sodium salt and compared with the orthophosphates. As a matter of fact, sodium dihydrogen phosphate shows the disadvantage that under the conventional processing conditions of the polymer mixture it easily condenses to agglomerates which, upon extrusion or injection-moulding of the polymer mixture, form annoying deposits. The disadvantage of zinc phosphate is that it reduces the activity of polymeric additives for the improvement of the impact strength, such as may be added to the polymeric mixtures according to the invention.

Therefore, a zinc or calcium hydrogen phosphate must be used as a transesterification inhibitor in the polymer mixture according to the invention. Suitable hydrogen phosphates are zinc-bis-(dihydrogen phosphate) and calcium-bis-(dihydrogen phosphate.)

The polymer mixture according to the invention comprises at any rate one or more of the following constituents:

- A) a polyalkylene phthalate
- B) a non-brominated aromatic polycarbonate or a brominated aromatic carbonate oligomer, polymer or copolymer or a mixture of a brominated aromatic carbonate oligomer, polymer or copolymer and a non-brominated aromatic polycarbonate and
- C) a hydrogen phosphate of zinc or calcium as a transesterification inhibitor.

In addition to the constituents mentioned herein before, the polymer mixture may comprise conventionally used additives. By way of example may be mentioned in particular polymeric additives to improve the impact strength, flame-retardant additives, reinforcing and non-reinforcing fillers, oxidation stabilisers, mould-release agents, processing additives, dyes and/or pigments. Moreover, the polymer mixture, in particular when it comprises a flame-retardant additive, for example, a brominated aromatic carbonate oligomer, polymer or copolymer, may also comprise antimony oxide as an auxiliary substance.

A) Polyalkylene phthalate

The invention relates to polymer mixtures which comprise a polyalkylene phthalate with units derived from an alkanediol and an aromatic dicarboxylic acid. The polyalkylene phthalate may comprise units derived from one or more alkanediol compounds. The polyalkylene phthalate also comprises units derived from one or more aromatic dicarboxylic acids. In addition to the alkanediol, the polyalkylene phthalate may comprise units derived from one or more other diol compounds or polyol compounds.

Polyalkylene phthalates generally comprise an excess of units derived from an alkanediol with respect to the optionally present units derived from other diol compounds or polyol compounds.

Suitable alkanediol compounds are, for example, ethanediol or butane-1,4-diol. In addition to units derived from aromatic dicarboxylic acids the polyalkylene phthalate may also comprise units derived from other dicarboxylic acids or polycarboxylic acids. However, the greater part of the units derived from acids is preferably derived from an aromatic dicarboxylic acid. Suitable aromatic dicarboxylic acids are terephthalic acid and isophthalic acid, preferably terephthalic acid.


As a polyalkylene phthalate is preferably used a polyalkylene phthalate having more than 70 mol % of units derived from terephthalic acid and butane-1,4-diol. It is also possible to use a mixture of two or more different polyalkylene phthalates.

B) Polycarbonate

The polymer mixture according to the invention comprises an aromatic polycarbonate or a brominated aromatic carbonate oligomer, polymer or copolymer or a mixture of a brominated aromatic carbonate

oligomer, polymer or copolymer and a non-brominated aromatic polycarbonate.

Aromatic carbonates are polymers known per se. They are generally prepared by reacting a dihydric phenol compound with a carbonate precursor, for example, phosgene, a halogen formate or a carbonate ester. Aromatic carbonates are polymers which comprise units of the formula



wherein A is a bivalent aromatic radical which is derived from the dihydric phenol used in the preparation of the polymer. Mononuclear or polynuclear aromatic compounds which comprise two hydroxy radicals each directly bonded to a carbon atom of an aromatic nucleus may be used as dihydric phenols in the preparation of the aromatic polycarbonates.

Examples of suitable dihydric phenols are: 2,2-bis-(4-hydroxy phenyl)propane; hydroquinone; resorcinol; 2,2-bis-(4-hydroxy phenyl)pentane; 2,4'-(dihydroxy diphenyl)methane; bis-(2-hydroxyphenyl)methane; bis-(4-hydroxyphenyl)methane; bis-(4-hydroxy-5-nitrophenyl)methane; 1,1-bis-(4-hydroxyphenyl)ethane; 3,3-bis(4-hydroxyphenyl)pentane; 2,2-dihydroxyphenyl; 2,6-dihydroxy-naphthalene; bis-(4-hydroxydiphenyl)sulphone; bis-(3,5-diethyl-4-hydroxyphenyl)sulphone; 2,2-bis-(3,5-dimethyl-4-hydroxyphenyl)diphenyl sulphone; 4,4'-dihydroxy diphenyl ether; dihydroxydiphenyl sulphone; bis-(4-hydroxyphenyl)diphenyl sulphone; 4,4'-dihydroxy diphenyl ether; 4,4'-dihydroxy-3,3'-dichlorodiphenyl ether; 4,4'-dihydroxy-2,5-dihydroxy diphenyl ether.

Other likewise suitable dihydric phenols are disclosed in US-A-2,999,835; 3,038,385; 3,334,154 and 4,131,575.

The aromatic polycarbonates may be prepared in a manner known per se: for example, by reacting a dihydric phenol with a carbonate precursor, for example, phosgene. For this purpose reference may be made to the United States Patent Specifications mentioned hereinbefore and to US-A-4,018,750 and 4,123,426. They may also be prepared by a transesterification as described in US-A-3,153,008.

The branched polycarbonates known per se as described, for example, in US-A-4,001,184 are also suitable.

Suitable aromatic polycarbonates are also the so-called polyester carbonates which are obtained by carrying out the polymerisation reaction in the presence of an ester precursor, for example, a difunctional ester-forming derivative thereof. These polyester carbonates have ester compounds and carbonate compounds in the polymeric chain. Polyester carbonates are described, for example, in US-A-3,169,121.

It is also possible to use a mixture of various polycarbonates as mentioned hereinbefore as an aromatic polycarbonate in the polymer mixtures according to the invention.

Brominated aromatic carbonate oligomer, polymer or copolymer: the polymer mixture according to the invention may comprise a brominated aromatic carbonate oligomer, polymer or copolymer instead of the non-brominated aromatic polycarbonate. It is also possible to replace a part of the non-brominated aromatic polycarbonate by a brominated aromatic carbonate. In that case the polymer mixture according to the invention comprises a mixture of a brominated aromatic carbonate oligomer, polymer or copolymer and a non-brominated aromatic polycarbonate. Brominated aromatic carbonate oligomers, polymers, copolymers are known per se as flame-retardants. Brominated aromatic carbonate oligomers, polymers, copolymers having a weight-averaged molecular weight between 500 and 70,000 may be used in the polymer mixture according to the invention. Suitable brominated aromatic carbonate oligomers, polymers or copolymers are described, for example, in US-A-3,936,400 and US-A-3,915,926.

C) Transesterification inhibitor

The polymer mixture according to the invention comprises a hydrogen phosphate, such as zinc or calcium (monohydrogen phosphate) or zinc or calcium - bis - (dihydrogen phosphate) as a transesterification inhibitor. The use of the said inhibitors provides the following advantages: a good suppression of the transesterification; no or hardly any influence on the activity of polymeric constituents to improve the impact strength when these are present in the polymer mixture (this in contrast with zinc ortho phosphate); the inhibitor used is a solid and as a result can more easily be compounded in an extruder than other known liquid inhibitors, for example, phosphoric acid and phosphorous acid; no discolouring (yellowing) of the polymer mixture as may occur when phosphoric acid is used and no greying when antimony oxide is

present (this does occur when phosphorous acid is used as an inhibitor). Compared with sodium dihydrogen phosphate, the inhibitor as used in the polymer mixture according to the invention provides the important advantage that no polycondensation of the phosphate occurs and hence no or hardly any deposits occur in the extrusion or injection - moulding.

5 In addition to the constituents mentioned herein before, the polymer mixture according to the invention may comprise any constituents conventionally used for such polymer mixtures. In particular may be mentioned the polymers which are generally known to improve the impact strength. These include in the first instance copolymers and graft copolymers which comprise rubber - like constituents. Examples are the core - shell graft polymers having a rubber - like core on which one or more monomers have been grafted.

10 Examples of further suitable constituents for the polymer mixture according to the invention are the following: flame - retardant additives other than the brominated aromatic carbonate oligomers, polymers or copolymers, reinforcing and non - reinforcing fillers, oxidation stabilisers, mould - release agents, processing additives, dyes and/or pigments mentioned hereinbefore.

The invention will now be described in greater detail with reference to the ensuing specific examples.

15 Examples I, II and III; comparative examples A and B

In the preparation of various polymer mixtures the following constituents were used:

- 20 - PBT: a polybutylene terephthalate having an intrinsic viscosity of 120 ml/g measured in a phenol - (1,1,2,2 - tetrachloroethane) mixture (60:40) at 25 °C.
- PC: an aromatic polycarbonate derived from phosgene and bisphenol A having an intrinsic viscosity of 58 ml/g measured in methylene chloride at 25 °C.
- PC-Br: a brominated aromatic carbonate copolymer derived from tetrabromobisphenol A, bisphenol A and phosgene having a bromine content of 22% by weight, having an intrinsic viscosity of 40 ml/g measured in methylene chloride at 25 °C.
- 25 - I.M.: a core - shell graft copolymer having a rubber - like "backbone" consisting for the greater part of a butadiene rubber on which methyl methacrylate and styrene have been grafted.
- Sb₂O₃: a mixture of 85% by weight of Sb₂O₃ and 15% by weight of a carrier polymer.
- PTFE: a mixture of polytetrafluoroethylene (20% by weight) and a non - brominated aromatic polycarbonate (80% by weight).
- 30 - Add.: a conventionally used antioxidation stabiliser and a mould - release agent.
- Inh.1.: finely ground zinc phosphate having a particle size of 1.4 micrometres; (Zn)₃(PO₄)₂·2H₂O. An inhibitor which was used for comparative experiments.
- Inh.2: zinc - bis - (dihydrogen phosphate) as inhibitor according to the invention; Zn(H₂PO₄)₂·2H₂O.
- 35 - Inh.3: calcium - bis - (dihydrogen phosphate) as inhibitor according to the invention Ca(H₂PO₄)₂.

The constituents mentioned hereinbefore in the quantities as indicated in the table hereinafter were compounded in a double - screw extruder, adjusted at an average temperature of 240 °C, extruded and chopped up to pellets. Test pieces were manufactured from the resulting pellets by injection - moulding to determine the following properties: the elongation at fracture (according to ASTM D 638); the notch impact strength according to Izod (ASTM D 256) and the melt viscosity index (MVI) at 250 °C under a load of 50N (according to ISO 1133). The test rods were injection - moulded under normal conditions, i.e. at an average adjusted temperature of 260 °C and a residence time in the cylinder of the injection - moulding machine of 2 minutes. Test rods were also injection - moulded to determine the Vicat value according to ISO R 306 B/120. The Vicat value was determined of rods which were injection - moulded in the manner described 45 hereinbefore, and of test rods which were injection - moulded under extra heavy conditions (average adjusted temperature 280 °C and a residence time of 2 minutes). When a transesterification occurs the results in a decrease of the Vicat value; the absolute value of the decrease is a measure of the transesterification. The lower the said value, the smaller the transesterification. The Vicat value itself, after injection - moulding under normal conditions, is also an indication for a possible transesterification. The 50 higher the said value, the smaller the transesterification will have been.

The found properties have also been recorded in the table hereinafter.

T A B L E

Example	A *	B	I	II	III
Composition (parts by weight)					
- PBT	54.8	54.2	54.7	54.5	54.6
- PC	15	15	15	15	15
- PC-Br	16	16	16	16	16
- Sb ₂ O ₃	3.5	3.5	3.5	3.5	3.5
- I.M.	10	10	10	10	10
- PTFE	0.15	0.15	0.15	0.15	0.15
- Add	0.6	0.6	0.6	0.6	0.6
- Inh.1	-	0.6	-	-	-
- Inh.2	-	-	0.1	0.3	-
- Inh.3	-	-	-	-	0.2
Properties					
- Izod impact strength (J/m) notched	720/920	260	640	670	720
- MVI (ml per 10 min.)					
after 4 min.	13 /7.1	12.5	11.5	10	11
after 8 min.	15.4/7.2	15	14	12	12
after 12 min.	15.7/7.0	17	16	13	13
Vicat value (°C)					
o after "normal" injectionmoulding	141.2/142	145.7	147.5	146.5	147.4
o after injection- moulding under aggravated conditions	138.6/122	145.4	146.5	147	146.5
o change in Vicat	2.6/20	0.3	1	0.5	0.9

* The composition according to example A has been prepared twice. Each of them has been tested separately. The values for both compositions have been indicated.

It may be seen from the table that inhibitors 2 and 3 have a good inhibiting effect; the decrease of the Vicat value is small and the Vicat value itself is comparatively high. Inhibitors 2 and 3 according to the invention further hardly showed any detrimental influence on the activity of the polymer which has been added to improve the impact strength. This appears from the favourable value for the impact strength according to Izod. Moreover, no deposits were formed during molding when inhibitors 2 and 3 were used.

In similar experiments with sodium dihydrogen phosphate deposits were formed.

Claims

- 5 1. A polymer mixture which comprises
 - A) a polyalkylene phthalate
 - B) a non-brominated aromatic polycarbonate or a brominated aromatic carbonate oligomer, polymer or copolymer or a mixture of a brominated aromatic carbonate oligomer, polymer or copolymer and a non-brominated aromatic polycarbonate and
 - 10 C) a transesterification inhibitor, in which the polymer mixture comprises a hydrogen phosphate of zinc or calcium as a transesterification inhibitor.
2. A polymer mixture as claimed in Claim 1, wherein the transesterification inhibitor is present in a quantity from 0.01 to 5 parts by weight per 100 parts by weight of the sum of constituent A and constituent B.
- 15 3. A polymer mixture as claimed in claim 1 wherein the transesterification inhibitor is zinc -bis- (dihydrogen phosphate).
4. A polymer mixture as claimed in claim 1 wherein the transesterification inhibitor is calcium -bis- (dihydrogen phosphate).
- 20 5. A polymer mixture as claimed in Claim 1, wherein the weight ratio of constituent A to constituent B is between 5 : 95 and 95 : 5.
- 25 6. A polymer mixture as claimed in Claim 1, wherein the polymer mixture comprises a polyalkylene phthalate having more than 70 mol% of units derived from terephthalic acid and butane-1,4-diol.
7. A polymer mixture as claimed in Claim 1, wherein the polymer mixture comprises a brominated aromatic carbonate oligomer, polymer or copolymer having a weight-averaged molecular weight from 500 to 70,000.
- 30 8. A polymer mixture as claimed in Claim 1, wherein the polymer mixture comprises a brominated aromatic carbonate oligomer, polymer or copolymer and an antimony oxide.
- 35 9. A polymer mixture as claimed in Claim 1, wherein the polymer mixture moreover comprises a polymer for improving the impact strength.
- 40 10. Articles formed from the polymer mixture as claimed in Claim 1.



European Patent
Office

EUROPEAN SEARCH REPORT

Application Number

EP 92 11 6872

DOCUMENTS CONSIDERED TO BE RELEVANT		
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim
A	US-A-4 532 290 (D.B.G. JAQUISS et al.) * Abstract; column 1, line 37 - column 3, line 21 *	1,2,5-7,10
D,A	FR-A-2 223 424 (TEIJIN LTD) * Claims 1-5; page 1, line 35 - page 2, line 24 *	1,5,6,10
A	EP-A-0 264 143 (GENERAL ELECTRIC CO.) * Claims 1-7; page 2, line 3 - page 3, line 26 *	1,2,5,6,9,10
A	US-A-4 981 898 (W.H. BASSETT) * Abstract; column 4, line 49 - column 5, line 10 *	1,10
A	US-A-4 972 015 (J.C. CARICO et al.) * Abstract; column 1, line 55 - column 2, line 9 *	1
A	DE-A-1 191 568 (ALLIED CHEMICAL CORP.) * Cl. *	1

CLASSIFICATION OF THE APPLICATION (Int. Cl.5)	
C 08 K	3/32
C 08 L	67/02
C 08 L	69/00 //
(C 08 L	67/02
C 08 L	69:00)
(C 08 L	69/00
C 08 L	67:02)

TECHNICAL FIELDS SEARCHED (Int. Cl.5)	
C 08 K	
C 08 L	

The present search report has been drawn up for all claims

Place of search	Date of completion of the search	Examiner
THE HAGUE	09-03-1993	KRISCHE D H T

CATEGORY OF CITED DOCUMENTS	
X : particularly relevant if taken alone	T : theory or principle underlying the invention
V : particularly relevant if combined with another document of the same category	E : earlier patent document, but published on, or after the filing date
A : technological background	() : document cited in the application
O : non-written disclosure	I : document cited for other reasons
P : intermediate document	& : member of the same patent family, corresponding document

EPO FORM 1503 (03/92) (P0401)

**This Page is Inserted by IFW Indexing and Scanning
Operations and is not part of the Official Record**

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

- ☒ **BLACK BORDERS**
- ☐ **IMAGE CUT OFF AT TOP, BOTTOM OR SIDES**
- ☒ **FADED TEXT OR DRAWING**
- ☒ **BLURRED OR ILLEGIBLE TEXT OR DRAWING**
- ☐ **SKEWED/SLANTED IMAGES**
- ☐ **COLOR OR BLACK AND WHITE PHOTOGRAPHS**
- ☐ **GRAY SCALE DOCUMENTS**
- ☐ **LINES OR MARKS ON ORIGINAL DOCUMENT**
- ☒ **REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY**
- ☐ **OTHER:** _____

IMAGES ARE BEST AVAILABLE COPY.

As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.